



ILACOLOR PE

Universal one-coat or two-coat exterior system with very pure, brilliant colour shades.

- Good thermoforming properties
- Good cleanability
- Good adhesion to the substrate
- Exclusively suitable for baking tin outer coating

Properties

Number of layers	1 - 2
Coating thickness	7 - 15 µm / 0.28 - 0.59 mils
Curing temperature to approx	260 °C / 500 °F
Staining resistance	★ ★ ★ ★ ★

Application

Application
Baking tins ✓ ✓ ✓

Substrate

Substrate	Pre-treatment	Suitability
aluminum	passivate free from chromium	✓ ✓ ✓
aluminized steel	passivate free from chromium	✓ ✓ ✓
ECCS	cleaning	✓ ✓ ✓



Cleaning and care instructions

Wipe the outside of the tin with a wet cloth. If the baking, grill or casserole dish is stubbornly dirty, clean it under hot water, a mild washing-up liquid and the fine side of a dishwashing sponge or a soft dishwashing brush. We strongly advise against using cleaning metal sponges. Always wipe the mould dry before storing.

Coated items can be cleaned in the dishwasher, although this is not recommended due to the aggressive cleaning agents. Cleaning by hand is preferable.